

## **LISTING OF THE CLAIMS**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) An electromagnetic noise suppressor having:  
a magnetic resonance frequency of 8 GHz or higher; and  
an imaginary part  $\mu''_H$  of complex magnetic permeability at 8 GHz which is higher than  
an imaginary part  $\mu''_L$  of complex magnetic permeability at 5 GHz,  
wherein the electromagnetic noise suppressor includes a composite layer including a  
complicated heterogeneous structure where a binding agent, being a resin or a rubber, and a  
magnetic material are integrated at the nanometer scale, wherein the composite layer includes a  
portion where a crystal lattice is observed to be made up of atoms of the magnetic material, a  
portion where only the binding agent is observed, and a portion where atoms of the magnetic  
material are observed to be dispersed in the binding agent without crystallizing.
2. (Canceled).
3. (Previously Presented) An electromagnetic noise suppressor according to claim 1,  
wherein the composite layer is formed by physically vapor-depositing the magnetic material onto  
the binding agent.
4. (Canceled).
5. (Original) An electromagnetic noise suppressor according to claim 3, wherein the  
binding agent is a resin or a rubber.
6. (Previously Presented) The electromagnetic noise suppressor according to claim 1,  
wherein the binding agent is a hardening resin.

7. (Original) The electromagnetic noise suppressor according to claim 3 wherein the binding agent is a hardening resin.

8. (Withdrawn) A method of manufacturing an electromagnetic noise suppressor, comprising:

physically vapor-depositing a magnetic material onto a binding agent to form a composite layer on the surface of the binding agent, thus obtaining an electromagnetic noise suppressor having a magnetic resonance frequency of 8 GHz or higher, and the imaginary part  $\mu''_H$  of complex magnetic permeability at 8 GHz higher than the imaginary part  $\mu''_L$  of complex magnetic permeability at 5 GHz.

9. (Withdrawn) A structure with an electromagnetic noise suppressing function, at least a part of which surface is covered with the electromagnetic noise suppressor of claim 1.

10. (Withdrawn) A structure with an electromagnetic noise suppressing function according to claim 9, wherein the structure is a printed wiring board having electronic components mounted thereon.

11. (Withdrawn) A structure with an electromagnetic noise suppressing function according to claim 9, wherein the structure is a semiconductor integrated circuit.

12. (Withdrawn) A method of manufacturing a structure with an electromagnetic noise suppressing function, comprising:

a coating process of coating at least a part of the surface of the structure with a binding agent; and

a vapor deposition process of physically vapor-depositing a magnetic material onto the binding agent to form a composite layer on the surface of the binding agent.

13. (Previously Presented) An electromagnetic noise suppressor having:

a magnetic resonance frequency of 8 GHz or higher; and  
an imaginary part  $\mu''_H$  of complex magnetic permeability at 8 GHz which is higher than  
an imaginary part  $\mu''_L$  of complex magnetic permeability at 5 GHz,  
wherein the electromagnetic noise suppressor includes a composite layer including a  
complicated heterogeneous structure where a binding agent and a magnetic material are  
integrated at the nanometer scale, wherein the composite layer includes a portion where a crystal  
lattice is observed to be made up of atoms of the magnetic material, a portion where the binding  
agent is observed without presence of the magnetic material, and a portion where atoms of the  
magnetic material are observed to be dispersed in the binding agent without crystallizing.

14. (New) An electromagnetic noise suppressor having:  
a magnetic resonance frequency of 8 GHz or higher; and  
an imaginary part  $\mu''_H$  of complex magnetic permeability at 8 GHz which is higher than  
an imaginary part  $\mu''_L$  of complex magnetic permeability at 5 GHz,  
wherein the electromagnetic noise suppressor includes a composite layer including a  
complicated heterogeneous structure where a binding agent and a magnetic material are  
integrated at the nanometer scale, wherein the composite layer includes a portion where a crystal  
lattice is observed to be made up of atoms of the magnetic material, a portion where only the  
binding agent is observed, and a portion where atoms of the magnetic material are observed to be  
dispersed in the binding agent without crystallizing, atoms of the magnetic material being  
separated by less than 10 nm.